

AKVACOAT 100 FLOOR PAINT

DESCRIPTION	Two-component waterborne floor paint for painting new, old and previously painted concrete surfaces. Akvacoat 100 is also suitable for cement plaster, brick and mineral plate surfaces.
EXAMPLES OF USE	Industrial, repair shop and storage floors subjected to light mechanical stress and chemicals. Akvacoat 100 is also suitable for garage floors, staircases, balconies, wash rooms, etc., and can be used as a floor and wall coating in food industry plants.
TECHNICAL DATA	Solids Volume: approx. 45%, depending upon the colour. Density: 1.3 kg/l for ready-to-use compound. Mixing Ratio: Clear Plastic Part, 1 Volume Part. Pigmented Hardener, 2 Volume Parts. Note: add the clear plastic part into the pigmented hardener and mix thoroughly. (Mixing time 3-5 minutes). Pot-life (23°C): approx. 1 hour. Temperature can affect the pot-life.
Colour Range	Tikkurila Professional Colour Swatch, Part 2 (Floors).
SPECIFICATIONS Preparation	Surfaces must be clean, dry and free from laitance, dirt, oil, wax, rust, all loose material and surface contamination. Note: Cleaning methods will depend upon the condition of the substrate to be painted. Repair all areas of failure, cracks, holes, etc., with either a suitable Tikkurila repair mortar or cement mortar. (Use only recommended concrete repair products for repairing concrete). Polished or glassy concrete surfaces should be mechanically abraded. Glossy and previously painted surfaces should be thoroughly flatted down. Note: The relative humidity of concrete and cement-rich substrates should be below 97%.
APPLICATION	Methods: brush or roller. Thinning: 5-15% with water.
Painting Conditions	All surfaces to be painted must be dry, the temperature of the air, surfaces, and paint should be at least 10°C, and the relative humidity of the air below 80%.
Painting	Ensure that the clear plastic part and pigmented hardener are thoroughly mixed and apply a priming coat of Akvacoat 100 thinned by up to 15% with water. Allow to dry for 16 hours and apply a finishing coat of Akvacoat 100, thinned by a maximum of 5% with water. Note: Ensure that the plastic part and pigmented hardener are thoroughly mixed prior to thinning with water.
Coverage	Priming: 5-7 m ² /l – Finishing: 7-10 m ² /l. Wet-film thickness approximately 100-200 µm per coat. Dry film thickness approximately 45-90 µm per coat. Actual spreading rates will depend upon many factors including texture, porosity and application method.

AKVACOAT 100 FLOOR PAINT

Drying Times	At 23°C and 50% relative humidity of the air: normally dust-dry in 6 hours and recoatable after 16 hours. Avoid hard stress (abrasion, etc.) to the surface during the first seven days after application.
Cleaning of Tools	Clean immediately after use with water and synthetic cleaner.
ENVIRONMENTAL	Empty cans should be recycled or disposed of in accordance with local regulations. Liquid waste should be destroyed according to the local regulations for hazardous waste.
TRANSPORT CLASSIFICATION	ADR/RID: plastic part 9 III hardener - Protect from frost.

lko/ome290304/101-s,0084041

The above information, based on laboratory tests and practical experience, has been proved valid at the date marked on the product data sheet. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As a manufacturer we cannot be responsible for any damages caused by using the product against our instructions or for inappropriate purposes.

For further information or advice contact:

Holman Specialist Paints Ltd
1 Central Trading Estate
Signal Way
Swindon SN3 1PD
Tel 01793 511537 FAX 01793 431142
www.holmanpaints.co.uk e-mail sales@holmanpaints.co.uk