

## UNICA SUPER LACQUER

### semi matt, gloss and semi-gloss

<b>DESCRIPTION</b>	Quick-drying urethane alkyd lacquer for use on interior and exterior wooden surfaces. Available in colourless and many other attractive colours.
<b>EXAMPLES OF USE</b>	Windows, doors, floors, etc., and above waterline on boats. Unica Super Lacquer can be used on surfaces previously coated with alkyd or acid catalysed lacquers.
<b>Colour Range</b>	Tikkurila Lacquer Color Card.
<b>SPECIFICATIONS</b> <b>Preparation</b>	Surfaces must be clean, dry, and free from grease, dirt, oil, wax, all loose material and surface contamination. Completely remove existing coatings that are in poor condition. Use recommended Tikkurila products as cleaning agents and suitable Tikkurila or other good quality wood fillers for filling cracks, joints, nail holes, blemishes, etc. Ensure that all glossy and filled surfaces are thoroughly flatted down. Always prime bare exterior wooden surfaces with Valtti Base prior to the application of Unica Super Lacquer.
<b>APPLICATION</b>	Methods: brush or spray. For airless spray: use a 0.009" – 0.013" (0.230 – 0.330mm) spray tip, and thin by up to 40% with white spirit. Thinning: by up to 40% with white spirit.
<b>Painting Conditions</b>	All surfaces to be painted must be dry, the moisture content of the wood below 20%, the temperature of the air at least +5°C, and the relative humidity of the air below 80%.
<b>Painting</b>	Stir thoroughly before use. Apply lacquer by brush or spray. On bare wooden surfaces use 1 coat of Unica Super Lacquer thinned by 5-10% with White Spirit as priming lacquer. For exterior situations use Valtti Base priming oil and Unica Super GLOSS Lacquer as priming lacquer. Apply one or two finishing coats of Unica Super Lacquer unthinned. On previously lacquered or varnished surfaces apply one or two coats of Unica Super Lacquer unthinned. Sand lightly between coats.
<b>Coverage</b>	12-14 m <sup>2</sup> /litre per coat. Actual spreading rates will depend upon many factors including texture, porosity, moisture content and application methods.
<b>Drying Times</b>	At 23°C and 50% relative humidity of the air: normally touch-dry in 6 hours and recoatable after 24 hours. Avoid hard stress (abrasion, etc.) to the surface during the first two weeks after application.

## UNICA SUPER LACQUER

**Cleaning of Tools**

Clean tools immediately after use with white spirit.

**PREVENT ENVIRONMENTAL  
DAMAGE**

Empty cans should be recycled or disposed of in accordance with local regulations. Liquid waste should be destroyed according to the local regulations for hazardous waste.

**TRANSPORT**

ADR/RID –

Iko/esi/ome300104/556-s,557-s

The above information, based on laboratory tests and practical experience, has been proved valid at the date marked on the product data sheet. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As a manufacturer we cannot be responsible for any damages caused by using the product against our instructions or for inappropriate purposes.

For further information or advice contact:

**Holman Specialist Paints Ltd**  
1 Central Trading Estate  
Signal Way  
Swindon SN3 1PD  
Tel 01793 511537 FAX 01793 431142  
[www.holmanpaints.co.uk](http://www.holmanpaints.co.uk) e-mail [sales@holmanpaints.co.uk](mailto:sales@holmanpaints.co.uk)